



Concrete Coatings & Floor Systems

APPLICATION BULLETIN

Kemiko® 100% Solids Self-Leveling Epoxy Fast Cure Clear (SS1202FF)

Description

Kemiko 100% Solids Self-Leveling Epoxy Fast Cure Clear (SS1202FF) is a two component, abrasion resistant epoxy coating that offers excellent adhesion to steel and concrete. Benefits of the product include: user friendly, 0 VOC, self-leveling, minimal odor and cures to a very hard, resilient high gloss film. These products can be applied as a finish coat on most interior surfaces. Kemiko SS1202FF is non-blushing in high humidity and comes in different variations to provide faster curing or UV resistance. SCAQMD VOC compliant.

Applications

Kemiko SS1202FF can be applied to properly prepared Kemiko primers and color coats. Typical applications include: concrete countertops, flooring in hospitals, food processing plants, warehouses, showrooms, petrochemical and chemical secondary containment and many other surfaces that require excellent physical and chemical properties. This product is not intended for UV exposed areas.

Surface Preparation

Concrete

Surface must be cured, dry and free from stains and laitance. All visible oil, grease or any other contaminants must be removed prior to application of coating. Surface preparation includes using concrete grinding and shot blasting to achieve a surface profile of CSP 3. The concrete should have a slight texture for the coating to achieve proper penetration and adhesion. Clean surface and ensure that all contaminants, dust, and debris have been removed. Check concrete preparation by applying water over a small area of the concrete surface (especially in areas that had oil and grease stains). If water beads on the surface, additional surface preparation is needed. If concrete darkens with no water beading on the surface, then the surface is ready to be coated. It is advisable to test a small area with sealer before starting the job to ensure that the substrate is compatible with this sealer choice.

Existing Coatings

Surface must be cured, dry and free from stains and laitance. All visible oil, grease or any other contaminants must be removed prior to application of coating. For best adhesion, the existing coating must be scuffed with a nonwoven abrasive pad, floor buffer with abrasive screen or orbital sander with sandpaper (80-120 grit) to achieve a rough surface profile. Clean area and wipe existing coating with a rag and acetone to ensure that all oil, grease or any other contaminants have been successfully removed. If existing coating is not a Kemiko product, consult with a Kemiko representative prior to application.

Warning: *Wear a NIOSH approved respirator to control toxin exposure. Scraping, sanding or removing old paint may release toxic lead dust. Exposure may lead to serious illness, such as brain damage, especially in children. Pregnant women should avoid exposure. Clean up carefully with a HEPA vacuum and a wet mop.*

Mixing Instructions

SS1202FF is packaged in such a way that a separate container is not needed for mixing. Using a mechanical jiffy-type mixer, blend SS1202FF Part A Resin component at slow speed (500-1000rpm) for 1-2 minutes until a homogenous mixture is achieved. Next, pour SS1202FF Part B Hardener component into the previously mixed Part A component. Ensure that all contents have been transferred. Now mix on slow to medium speed (500-1000rpm) for 1-2 minutes. Avoid fast, aggressive mixing as that may entrap air bubbles into the system. Scrape sides of container and then mix for an additional 1-2 minutes, ensuring material is thoroughly blended.

Mixing Tips

- To help reduce material loss during transfer, use of a can opener to make a hole on the rim of the SS1202FF Part B Hardener component is recommended.
- Do not mix product by hand; only use a mechanical mixer. Hand mixing does not properly incorporate the components.
- For best results, prior to mixing, have material as close as possible to an ambient temperature of 75°F (24°C).



Concrete Coatings & Floor Systems

APPLICATION BULLETIN

Kemiko® 100% Solids Self-Leveling Epoxy Fast Cure Clear (SS1202FF)

Application Instructions

This product can be applied using one of the methods outlined below. Tape off any area that does not require coating. Pour contents in "ribbons" or "strips" across the surface to be coated. Spread material out with a brush or roller to the recommended wet film thickness. A second coat can be applied up to 24 hours after the first coat has reached a dry to touch state. Do not thin material.

- Brush** Use high quality bristle brush for best film properties
- Roller** Use lambswool or similar cover with phonolic core, 3/8"-1/2" nap. De-lint roller prior to use
- Spray** This material is not intended for spray applications

Clean Up

Use acetone or denatured alcohol to clean tools. Use warm water and mild soap to clean hands and skin.

Environmental Conditions

Apply between 50°F-80°F (10°C-27°C) and 5°F (3°C) above dew point. Avoid using in direct sunlight. Do not apply on rainy or foggy days.

Storage Conditions

Store between 50°F-100°F (10°C-32°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition.

Safety

Care should be taken when using this product. During application, use proper protective equipment including, but not limited to: protective eyewear, proper respirator and protective gloves. Ensure work spaces are well ventilated. Refer to the Technical Bulletin for technical information. Refer to product label and SDS carefully for more detailed safety information prior to use or handling.

Disclaimer

Information provided in this Technical Bulletin is based on laboratory testing and is used as a guideline only. Customer should test the material for their specific application and under their application conditions before using the product on a project.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.

Contact EPMAR for any additional application information



Epmar Corporation
13240 Barton Circle, Whittier, CA 90605-3254
Ph: 562.946.8781 / Fax: 562.944.9958
www.epmar.com / www.kemiko.com

Rev100118