



Concrete Coatings & Floor systems

TECHNICAL BULLETIN Kemiko® Stone Tone™ Buff On Wax Solvent Based (42 Series)

Description

Kemiko® Stone Tone™ Buff On Wax Solvent Based (42 series), also known as Stone Tone™ Wax, is a penetrating wax especially formulated to produce a low leather-like sheen finish with high protection, high durability, and unsurpassed water resistance. It is designed to be applied over unsealed porous-type concrete such as over bare concrete as well as Kemiko® Stone Tone™ Stained concrete. This product is intended only for interior use. This product is not intended for use in SCAQMD regions.

Applications

Kemiko® Stone Tone™ Buff On Wax 42 series can be applied over unsealed concrete and masonry surfaces. Typical applications include bare concrete, Stone Tone™ Acid Stained concrete, pigmented concrete, tile, and brick.

Physical Characteristics

Kit Size	1 gallon available
Colors Available	Clear Only
Volume Solids	22.15% volume solids
VOC Contents	<603 g/L (theoretical)
Specific Gravity	0.919 (theoretical)
Film Thickness	This product is not designed for provide a film
Coverage Per Kit	1gal: 300ft ² - 500ft ² (27.9m ² - 46.5m ²) Note: Coverage rates will vary depending on surface texture and porosity Suggested coverage is for non-diluted material. Dilutions will increase coverage
Dry/Recoat Time	Dry to Touch: 10-20 minutes Light Foot Traffic: 45-60 minutes Heavy Traffic: 3-4 hours Full Chemical & Physical Resistance Cure: 3-5 days Recoat Window: Within 24 hours after product reaches Dry to Touch state Note: Product tested at 70°F and 30% RH. Dry and recoat times will depend on temperature, humidity and other conditions relative to the environment.
Odor	Sweet mild solvent odor
Primers	No primer required
Thinning	Do not thin product
Clean Up	Clean tools with acetone, MEK, mineral spirits, paint thinner, or denatured alcohol
Shelf Life	12 months from date of manufacture



Concrete Coatings & Floor systems

TECHNICAL BULLETIN Kemiko® Stone Tone™ Buff On Wax Solvent Based (42 Series)

Packaging Description

Weight per Kit:

1Gal: 7.24lbs (3.28kg)

Kemiko® Easy Shine™ contains:

1Gal (3.78L) of product in a premeasured 1 gallon (3.78L) container

Environmental Conditions

Apply between 50°F - 85°F (10°C - 29°C) and 5°F (3°C) above dew point. Avoid using in direct sunlight. Do not apply on rainy or foggy days.

Storage Conditions

Store between 50°F - 100°F (10°C - 37.8°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition.

Safety

Care should be taken when using this product. Contents are flammable. Ensure no sources of ignition are in proximity to the product prior to application. Turn off any pilot lights, water heaters or any other auto-ignition sources in the area. Do not smoke around the product while applying or while it is drying. During application, use proper protective equipment including, but not limited to; protective eye wear, proper respirator, and protective gloves. Ensure work spaces are well ventilated. Refer to the Application Bulletin for application information. Refer to product label and SDS carefully for more detailed safety information prior to use or handling.

Disclaimer

Information provided in this technical bulletin is based on laboratory testing and is used as a guideline only. Customer should test the material for their specific application and under their application conditions before using the product on a project.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product that is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.



Contact us for any additional application information.

EPMAR Corporation - A Quaker Houghton Company

9930 Painter Ave, Whittier, CA 90605-3254

P: 562.946.8781 F: 562.944.9958

epmar.com | kemiko.com

Rev03.2021